

PERFORMANCE OF STONE MASTIC ASPHALT INCORPORATING STEEL FIBER.

NUR EZREEN BINTI JASNI

B. ENG(HONS.) CIVIL ENGINEERING

UNIVERSITI MALAYSIA PAHANG



STUDENT'S DECLARATION

I hereby declare that the work in this thesis is based on my original work except for quotations and citations which have been duly acknowledged. I also declare that it has not been previously or concurrently submitted for any other degree at Universiti Malaysia Pahang or any other institutions.

(Student's Signature)

Full Name : NUR EZREEN BINTI JASNI

ID Number : AA15194

Date : 31 MAY 2019

PERFORMANCE OF STONE MASTIC ASPHALT INCORPORATING STEEL
FIBER

NUR EZREEN BINTI JASNI

Thesis submitted in partial fulfillment of the requirements
for the award of the
B. Eng (Hons.) Civil Engineering

Faculty of Civil Engineering & Earth Resources
UNIVERSITI MALAYSIA PAHANG

MAY 2019

ACKNOWLEDGEMENTS

In the name of Allah S.W.T, the Most Gracious and the Most Merciful.

First and foremost, I am so grateful to Allah S.W.T, for giving me the strength and opportunity to complete my Final Year Project entitled “The Performance of Stone Mastic Asphalt Incorporating Steel Fiber”.

I would like to express my deep gratitude to my advisor, Dr. Khairil Azman Bin Masri for his guidance, motivation, enthusiastic encouragement and useful critiques of this research work. I would also like to thank highway and traffic laboratory technicians for their assistance in guiding the works throughout the process of completing this Final Year Project. I also owe a lot to all the lecturers in Civil and Environmental Engineering Department who has taught me within these four years.

Last but not least, my special dedication goes to my mother and my father for their prayers and support. Also, my special thanks to my beloved family for their love and trust. Lastly, thanks to all of my friends who had involved directly or indirectly, for their encouragements in the completion of this report.

ABSTRAK

Batu Mastic Asphalt (SMA) adalah jurang campuran campuran gred panas yang mengandungi peratusan besar agregat dan pengisi bitumen mastic. Biasanya campuran SMA telah ditambah dengan pengikat polimer yang diubah suai. SMA menderita pengaliran parah yang teruk akibat jurang campuran agregat yang bergred yang cenderung memberikan batu yang stabil ke batu batu termasuk campuran kaya mastic asphalt. Serat Keluli adalah bahan tambah yang akan menstabilkan mortar asphalt dan menebalkan bitumen untuk mengelakkan pengikat berlebihan. SMA baik untuk digunakan dengan kehadiran serat untuk meningkatkan ketahanan campuran SMA. Oleh itu, kertas ini membentangkan keberkesanan menggunakan gentian keluli dalam meningkatkan daya tahan di lapisan permukaan turapan SMA adalah lapisan yang secara langsung terdedah kepada kesan lalu lintas. Untuk membuat campuran SMA, spesimen dipadatkan dengan menggunakan 50 pukulan pada setiap muka menggunakan pemadat Marshall pada suhu pemadatan tertentu. Kemudian, spesimen yang telah diubah suai telah diuji untuk menilai prestasi dari segi ujian Los Angeles Abrasion, Ujian Kestabilan Marshall, Ujian resilient Modulus dan Dynamic Creep. Keputusan menunjukkan bahawa spesimen yang mengandungi gentian keluli boleh digunakan dalam kursus pengikat jalan kaki yang fleksibel kerana kesan kestabilan yang positif. Hasilnya menunjukkan bahawa penambahan gentian 0.3% membawa kepada kestabilan dan kekukuhan yang lebih baik sementara, penambahan gentian 0.5% untuk dinamik modulus berdaya tahan meningkat pada 25 °C dan penambahan 0.4% pada 40 °C. Kesimpulannya, penambahan serat keluli dalam campuran mempunyai potensi untuk memperbaiki masalah pengikat. menjana campuran turapan yang lebih baik, disarankan untuk membuat kajian lanjut pada masa akan datang menggunakan serat pada suhu yang dipadatkan dan jumlah pukulan yang berlainan.

ABSTRACT

Stone Mastic Asphalt (SMA) is a gap graded hot mix asphalt that contains a large percentage of coarse aggregate and bitumen filler mastic. Usually, SMA mixes has been added with polymer modified binder. SMA is suffer with severe binder drain down due to the gap graded aggregates mixtures that tends to provide a stable stone to stone skeleton including a rich mixture of asphalt mastic. The Steel Fiber is the additive that will stabilize the asphalt mortar and thicken the bitumen to prevent excessive binder drain down. SMA is good to be used in the presence of fiber to enhance the durability of the SMA mixes. Thus, this paper is presenting the effectiveness of using steel fiber in improving the durability at the surface layer of SMA pavement, which are directly subjected to the traffic effects. To prepare SMA mixtures, Specimens were compacted by applying 50 blows on each face using a Marshall Impact compactor at specific compaction temperatures. Then, the modified specimens were tested to investigate the performance in terms of Los Angeles Abrasion Test, Marshall Stability Test, Resilient Modulus Test and Dynamic Creep. The results indicated that the specimens incorporating steel fiber can be used in binder course of flexible pavement because of its positive stability impact. The result shows that the addition of 0.3% fiber lead to better stability and stiffness while, 0.5% fiber for resilient and enhanced modulus dynamic creep at 25°C and 0.4% fiber at 40°C. Thus, it can be concluded that the addition of steel fiber in the mixture has the potential to improve binder drain down problem. In order to generate a better pavement mixes in the future, it is advisable to have a further research using the fiber at different compacted temperature and different number of blows.

TABLE OF CONTENT

DECLARATION

TITLE PAGE

ACKNOWLEDGEMENTS **1**

ABSTRAK **2**

ABSTRACT **3**

TABLE OF CONTENT **4**

LIST OF TABLES **8**

LIST OF FIGURES **9**

LIST OF ABBREVIATIONS Error! Bookmark not defined.

CHAPTER 1 INTRODUCTION **10**

1.1 Introduction 10

1.2 Problem Statement 11

1.3 Objectives 12

1.4 Scope of Study 12

1.5 Significant of Study 13

CHAPTER 2 LITERATURE REVIEW **14**

2.1 Introduction 14

2.2 Type of Pavement 14

2.2.1 Flexible Pavement 14

2.2.2 Rigid Pavement 16

2.2.3 Overview history of roads 17

2.3 Type of Flexible Pavement 19

2.3.1	Dense Graded Asphalt	19
2.3.2	Porous Asphalt	19
2.3.3	Polymer	20
2.3.4	Stone Mastic Asphalt	21
2.4	Overview of Stone Mastic Asphalt	21
2.5	Additive	23
2.5.1	Nanosilica	23
2.5.2	Sasobit	24
2.5.3	Anti-stripping Agent	24
2.5.4	Steel Fiber	25
2.5.5	Kenaff Fiber	26
2.6	Overview Steel Fiber	27
2.7	Performance of Stone Mastic Asphalt	27
CHAPTER 3 METHODOLOGY		29
3.1	Introduction	29
3.2	Research Framework	29
3.3	Materials	31
3.4	Binder Properties	31
3.4.1	Softening Point Test	32
3.4.2	Penetration Test	34
3.4.3	Ductility Test	35
3.5	Aggregate Properties	36
3.5.1	Sieve Analysis Test	36
3.5.2	Flakiness and Elongation	37
3.5.3	Aggregate Impact Value Test	37

3.5.4	Aggregate Crusing Value Test	39
3.5.5	Los Angeles Abrasion Test	40
3.6	Determination of Optimum Binder Content	41
3.6.1	Marshall Mix Design	42
3.7	Mixture Performance Test	43
3.7.1	Marshall Stability Test	43
3.7.2	Los Angeles Abrasion Test	44
3.7.3	Resillient Modulus Test	45
3.7.4	Dynamic Creep Test	46
3.8	Analysis and Discussion	47
CHAPTER 4 RESULTS AND DISCUSSION		48
4.1	Introduction	48
4.2	Binder Properties Test	48
4.2.1	Softening Point Test	48
4.2.2	Penetration Test	49
4.2.3	Ductility Test	49
4.3	Aggregate Test	49
4.3.1	Sieve Analysis Test	49
4.3.2	Flakiness and Elongation	50
4.3.3	Aggregate Impact Value Test	51
4.3.4	Aggregate Crushing Value Test	51
4.3.5	Los Angeles Abrasion Test	52
4.4	Laboratory Evaluation (Performance Test)	52
4.4.1	Marshall Stability Test	52
4.4.2	Los Angeles Abrasion Test	53

4.4.3	Resilient Modulus Test	55
4.4.4	Dynamic Creep Test	58
4.5	Optimum Fibre Content Determination by Ranking	60
CHAPTER 5 CONCLUSION		62
5.1	Introduction	62
5.2	Recommendation	63
REFERENCES		65
APPENDIX A SAMPLE APPENDIX 1		69
LOS ANGELES ABRASION TEST		70
MARSHALL STABILITY TEST		71
RESILIENT MODULUS TEST AT 25°C		74
RESILIENT MODULUS AT 40°C		75
DYNAMIC CREEP TEST AT 25°C		76

LIST OF TABLES

Table 4. 1	Softening Point Test	48
Table 4. 2	Penetration Test	49
Table 4. 3	Gradation Limit for SMA 20	50
Table 4. 4	Flakiness and Elongation Index of Aggregate	51
Table 4. 5	Aggregate Impact Value Test	51
Table 4. 6	Aggregate Crushing Value Test	51
Table 4. 7	Loss Angeles Abrasion Test	52
Table 4. 8	Marshall Stability Test	53
Table 4. 9	Comparison between Marshall Test Results According to Public Work Department (2008)	53
Table 4. 10	Loss Angeles Abrasion Test	54
Table 4. 11	Resilient Modulus Test at 25°C	56
Table 4. 12	Resilient Modulus Test at 40°C	56
Table 4. 13	Ranking of Performance Test	61

LIST OF FIGURES

Figure 2. 1	Flexible Pavement Layers	15
Figure 2. 2	Rigid Pavement layers	16
Figure 2. 3	Dense graded asphalt	19
Figure 2. 4	Stone Mastic Asphalt	21
Figure 2. 5	Stone Mastic Asphalt aggregate decomposition	22
Figure 2. 6	Kenaff Fiber	26
Figure 2. 7	Mineral Steel Fiber	27
Figure 3. 1	Methodology Flow Chart	30
Figure 3. 2	Softening Point Test	32
Figure 3. 3	Bitumen poured in the brass rings	33
Figure 3. 4	The specimens in water bath.	33
Figure 3. 5	Specimen while testing	34
Figure 3. 6	Penetrometer	34
Figure 3. 7	Ductilometer	35
Figure 3. 8	Sieve Analysis Shaker	36
Figure 3. 9	Flakiness and Elongation Materials	37
Figure 3. 10	Aggregate Impact Testing Machine	37
Figure 3. 11	Compression Testing Machine	39
Figure 3. 12	Los Angeles Abrasion Machine	40
Figure 3. 13	Marshall Compression Machine	43
Figure 3. 14	Los Angeles Abrasion Machine Testing	44
Figure 3. 15	Universal Testing Machine(UTM25) for Resilient Modulus Test	45
Figure 3. 16	Universal Testing Machine(UTM) for Dynamic Creep Testing	46
Figure 4. 1	Percentage of Abrasion vs Number of Revolution	55
Figure 4. 2	Resilient Modulus vs Amount of Steel Fibre at 25°C	57
Figure 4. 3	Resilient Modulus vs Amount of Steel Fibre at 40°C	58
Figure 4. 4	Strain vs Cycle(s) at 25°C	60
Figure 4. 5	Strain vs Cycle(s) at 40°C	60

CHAPTER 1

INTRODUCTION

1.1 Introduction

Pavement is necessary in any country. Pavement can be defined as the most upper surface of the road. Road, runway, street and etc are the best example of the roads pavement that is hard surface. According to other structure in Civil Engineering, pavement is ordinary to be sturdy and durable to withstand the heavy traffic loads. Flexible pavement and rigid pavement are both classified as road pavements (Mohod and Kadam 2016). The rigid pavement is fabricated of Portland cement concrete while the flexible pavement are the mixture of aggregates, bitumen and soil layers. According to (Pereira and Pais 2017), the subgrade, Subbase, base course and the surfacing are the main layers in flexible pavement. Flexible pavement is a mixture of aggregates and bituminous material that is compacted with granular that poured on the top level. In Malaysia flexible pavement are usually used for the roads. Flexible pavement is just like its name “flexible” since the total pavement structure bends and deflects due to its load. In order to accommodate the flexing, It is also normally composed of several layers of materials with flexible surface course. Flexible pavement also plays it function that will distribute imposed loads over the large area of natural soils but smaller area distribution to be compared to rigid pavements.

Hot mixed Asphalt (HMA) is the asphalt aggregate mixture that usually produced at batch mixing facility and must be mixed, spread and laid at an elevated temperature that in range of 140°C to 160°C (Kim, Lee et al. 2012). Hot Mixed Asphalt (HMA) is still the process of heating aggregates and asphalt binder.

In general, the asphalt binder is mixed with the aggregate at desired temperature to fully coated aggregate and binder and prepare for suitable for paving. The viscosity will turn out lower at lower temperature and lets the aggregate to be fully coated compared to what is conventionally required in HMA production (Kilas, Vaitkus et al.

2010). These will contribute to the combined weakening of the mastic and weakening of the aggregate-mastic bond.

In order to improve the performance of asphalt mixtures, the using of using fiber is not new in industries. It is continuously being introduced in industries as a new fiber materials such as steel fiber, carbon fiber, cellulose fiber, kenaf fiber, bamboo fiber, etc. Steel fiber were added to enhance the performance of the stone mastic asphalt. According to (Akbulut, Woodside et al. 2000), Fibers such as cellulose, mineral and polyester fibers in the mixture were used to stabilize the mastic asphalt and reduces binder drain down especially for stone mastic asphalt or open graded friction course during the material transportation and paving (Hassan, Al-Oraimi et al. 2005).

1.2 Problem Statement

In this new era technologies, fibers has been used widely in stone mastic asphalt (SMA). Stone Mastic Asphalt was designated to be a hot mixture asphalt with high content of course aggregate, high binder content mortar and fibers additive (Arshad, Masri et al. 2017). According to JKR/SPJ/2008 stone mastic asphalt comprises 65% of course aggregate to meet the requirement before used in Malaysia. The origin purpose of using stone mastic asphalt is that it can improved rutting resistant and resist studded tyre wear(Mahrez and Karim 2010). Besides that, factors such as heavy traffic loads tends to effect the performance of SMA because SMA always shown to give better resistance to plastic deformation and good low temperature properties. SMA is categorized by gap-graded in term of aggregate gradation and high content of course aggregate. Thus, the asphalt concrete facing a binder drain down problem due to its aggregate gradation that caused by the high content of course aggregate (Ahmedzade and Sengoz 2009). A common method to solve this problem was by modifying the asphalt mixtures by adding Steel Fiber. Since Steel Fiber was an additives that tends to stabilize improvement of the properties for civil engineering materials, this study intends to promote Steel Fiber as an additive in asphalt mixture in order stabilize the asphalt mixture and reducing the binder drain down. Thus, the mixtures ensure the homogeneity of the asphalt mixture.

1.3 Objectives

The aim of this study is to enhance the performance of Stone Mastic Asphalt (SMA) with the existence of Steel Fiber. Among the objectives are:

- a) To determine the materials properties of PEN (60-70) of asphalt binder and aggregate SMA20.
- b) To determine the optimum Steel Fiber content for Stone Mastic Asphalt 20 by evaluating the performance test.
- c) To evaluate the mechanical performance of Stone Mastic Asphalt 20 incorporating Steel Fiber.

1.4 Scope of Study

This study focuses to perform a laboratory study to evaluate the performance of stone mastic asphalt incorporating steel fibers. This research undergoes laboratory testing on the material properties test of asphalt binder and aggregate. First and foremost, for the aggregates, it undergoes sieve analysis test, Los Angeles Abrasion Value Test, Aggregate Impact Value Test, Aggregate Crushing Value Test, Flakiness and Elongation test. The testing for the asphalt binder were the physical properties test such as penetration test at 25°C, softening point test and ductility test. By using the results from the physical properties test, the Penetration Index (PI) and the temperature susceptibility of asphalt binders can be determine using nomograph of PI(SP/pen). Marshall Mix Design test also was done in order to find the value of Optimum Bitumen Content.

50 mixture identical specimens were prepared. The steel fiber will be mix with the virgin bitumen 60/70 penetration grade for the whole specimen preparations. 50

REFERENCES

Ahmedzade, P. and B. Sengoz (2009). "Evaluation of steel slag coarse aggregate in hot mix asphalt concrete." Journal of hazardous materials **165**(1-3): 300-305.

Akbulut, H., et al. (2000). Polymer modified cellulose pellet fiber in bituminous mixtures. Proceedings of 2nd Eurasphalt & Eurobitume Congress, on CD-ROM, Barcelona.

Akisetty, C. (2008). "Evaluation of warm asphalt additives on performance properties of CRM binders and mixtures."

Al-Ridha, A. S., et al. (2014). "Effect of steel Fiber on the Performance of Hot Mix Asphalt with Different Temperatures and Compaction." Australian Journal of Basic and Applied Sciences **8**(6): 123-132.

Aman, M. Y. and M. O. Hamzah (2014). "Effects of anti-stripping additives on moisture sensitivity of warm porous asphalt mixtures." International Journal of Construction Technology and Management **1**(1): 1-7.

Arrieta, V. S. and J. E. C. Maquilón (2014). "Resistance to degradation or cohesion loss in Cantabro test on specimens of porous asphalt friction courses." Procedia-Social and Behavioral Sciences **162**: 290-299.

Arshad, A., et al. "EVALUATION OF NANOSILICA MODIFIED STONE MASTIC ASPHALT."

Arshad, A. K., et al. (2016). "Performance of stone mastic asphalt mix using selected fibres." Jurnal Teknologi **78**(7-2): 99-103.

Arshad, A. K., et al. (2017). "Investigation on Moisture Susceptibility and Rutting Resistance of Asphalt Mixtures incorporating Nanosilica Modified Binder." PERTANIKA JOURNAL OF SCIENCE AND TECHNOLOGY **25**: 19-30.

Becker, Y., et al. (2001). Polymer modified asphalt. Vision tecnologica, Citeseer.

Behiry, A. E. A. E.-M. (2013). "Evaluation of steel slag and crushed limestone mixtures as subbase material in flexible pavement." Ain Shams Engineering Journal **4**(1): 43-53.

Chen, H., et al. (2009). "Evaluation and design of fiber-reinforced asphalt mixtures." Materials & Design **30**(7): 2595-2603.

Dewangan, A., et al. (2013). "The significance of geotextile in unpaved roads with special reference to stress analysis." International Journal of Current Engineering and Technology **3**(1): 168-178.

Ezzat, H., et al. (2016). "Evaluation of asphalt binders modified with nanoclay and nanosilica." Procedia engineering **143**: 1260-1267.

Hainin, M., et al. (2018). Performance of Hot Mix Asphalt Mixture Incorporating Kenaf Fibre. IOP Conference Series: Earth and Environmental Science, IOP Publishing.

Hassan, H. F., et al. (2005). "Evaluation of open-graded friction course mixtures containing cellulose fibers and styrene butadiene rubber polymer." Journal of Materials in Civil Engineering **17**(4): 416-422.

Hurley, G. C. and B. D. Prowell (2005). "Evaluation of Sasobit for use in warm mix asphalt." NCAT report **5**(6): 1-27.

Karami, M., et al. (2018). "Laboratory experiment on resilient modulus of BRA modified asphalt mixtures." International Journal of Pavement Research and Technology **11**(1): 38-46.

Katman, H. Y., et al. (2015). "Evaluation of permanent deformation of unmodified and rubber-reinforced SMA asphalt mixtures using dynamic creep test." Advances in Materials Science and Engineering **2015**.

Khope, R. A. and M. V. Mohod "Analysis of Rigid Pavement Casted with Recycled Aggregates Under Static Loading."

Kilas, M., et al. (2010). "Warm Mix Asphalts research, analysis and evaluation."

Kim, Y., et al. (2012). "Performance evaluation of warm-and hot-mix asphalt mixtures based on laboratory and accelerated pavement tests." Advances in Materials Science and Engineering **2012**.

Liu, Q. and D. Cao (2009). "Research on material composition and performance of porous asphalt pavement." Journal of Materials in Civil Engineering **21**(4): 135-140.

Mahrez, A. and M. R. Karim (2010). "Fatigue characteristics of stone mastic asphalt mix reinforced with fiber glass." International Journal of the Physical Sciences **5**(12): 1840-1847.

Mathew, T. V. and K. Krishna Rao (2007). "Traffic Data Collection." Introduction to Transportation Engineering, NPTEL.

Mohod, M. V. and K. Kadam (2016). "A comparative study on rigid and flexible pavement: a review." IOSR Journal of Mechanical and Civil Engineering (IOSR-JMCE) **13**(3): 84-88.

Muniandy, R. and B. B. Huat (2006). "Laboratory diametral fatigue performance of stone matrix asphalt with cellulose oil palm fiber." American Journal of Applied Sciences **3**(9): 2005-2010.

Nunn, M. (1994). "Evaluation of stone mastic asphalt (SMA): A high stability wearing course material." TRL Project Report(PR 65).

Pereira, P. and J. Pais (2017). "Main flexible pavement and mix design methods in Europe and challenges for the development of an European method." Journal of Traffic and Transportation Engineering (English Edition) **4**(4): 316-346.

Putman, B. J. and L. C. Kline (2012). "Comparison of mix design methods for porous asphalt mixtures." Journal of Materials in Civil Engineering **24**(11): 1359-1367.

Qiu, Y. and K. Lum (2006). "Design and performance of stone mastic asphalt." Journal of transportation engineering **132**(12): 956-963.

Samsudin, M. S., et al. (2016). "Microstructure of nanosilica modified binder by atomic force microscopy." Jurnal Teknologi **78**(7-3): 33-44.

Sengul, C. E., et al. (2013). "Evaluation of SBS modified stone mastic asphalt pavement performance." Construction and Building Materials **41**: 777-783.

Serin, S., et al. (2012). "Investigation of usability of steel fibers in asphalt concrete mixtures." Construction and Building Materials **36**: 238-244.

Singh, D., et al. (2017). "Evaluating performance of PPA-and-elvaloy-modified binder containing WMA additives and lime using MSCR and LAS tests." Journal of Materials in Civil Engineering **29**(8): 04017064.

Walsh, I. D. (2011). "The role of durability of surfacing in highway asset management." The International Journal of Pavement Engineering & Asphalt: 36.

Yang, J. and S. Tighe (2013). "A review of advances of nanotechnology in asphalt mixtures." Procedia-Social and Behavioral Sciences **96**: 1269-1276.

Yildirim, Y. (2007). "Polymer modified asphalt binders." Construction and Building Materials **21**(1): 66-72.